

Datasheet ATC

Composition

Fabric	: Polyamide/Elasthan jersey	120 gr/m ²
Coating	: PU topcoat /plasticized PVC / PVC foam, flame retardant	<u>430 gr/m²</u>
Thickness	: -	550 gr/m ² ± 7.5%

Properties

		Length	Width	
Tensile strength	DIN53354	275 N/5cm	240 N/5cm	± 20 %
Elongation	DIN53354	225 %	275 %	± 25 %
Tear strength	DIN53356	30 N		± 25 %
Adhesion	DIN53357	> 40 N/5cm		
Impermeability to water	DIN53886	> 100 cm		
Colorfastness	ISO 105	> 6		

Flame retardancy: FMVSS 302 <100 mm/min

Special properties

Due to the use of migration resistant and hydrolysis resistant polymeric plasticizers the material is much better resistant against (skin)grease and moisture (urine) than traditional artificial leather. This material will harden less quickly than traditional artificial leather.

Washing instructions



Handwash

Clean with damp piece of cloth and household soap (solvent free).

Don't fold and put the material away when wet.

Remarks

Small differences in color and gloss are possible (hold recipe numbers separated).

Reproducibility Color: unicolor < 1, printed < 1.5, dualcolor < 2 (Delta E CIE-lab 1976 D65).

Don't use material in applications that overstretch the material.

Date: 26/9/2018

Datasheet date: 6/6/2013

ABN AMRO BANK: 47.37.10.978

IBAN: NL94ABNA0473710978

BIC: ABNANL2A

ING BANK: 903250

IBAN: NL45INGB0000903250

BIC: INGBNL2A

BTW/VAT: NL005840247B01

Chamber of Commerce: 08036741

Our general terms and conditions are applied to all our offers, orders and agreements. A copy is available on request.



Management
System
ISO 9001:2015

www.tuv.com
ID 9108622561