

## Datasheet BRU

### Composition

Fabric	: Glass fabric	630 gr/m <sup>2</sup>
Coating	: Double sided, aluminium pigmented polyurethane, flame retardant	<u>60 gr/m<sup>2</sup></u>
Thickness	: -	690 gr/m <sup>2</sup> ± 5%

### Properties

		Length	Width	
Tensile strength	DIN53354	6000 N/5cm	5500 N/5cm	± 20 %
Elongation	DIN53354			
Tear strength	DIN53356	>100N	>100N	
Adhesion	DIN53357			
Impermeability to water	DIN53886			
Colorfastness	ISO 105	> 6		

Flame retardancy: NFP 92-503 M1

### Special properties

Maximum temperature 550 ° C.  
 Coating degradation starting from about 200 ° C.  
 Maximum continuous temperature 150 ° C.  
 When heated the vaporization is low and free of halogen.

### Washing instructions



Clean with damp piece of cloth and solvent free cleanser.  
 Don't fold and store when wet.

### Remarks

Differences in color and gloss are possible (Keep recipe numbers separated).

Date: 10/9/2024

IBAN: NL94ABNA0473710978  
 BIC: ABNANL2A  
 BTW/VAT: NL005840247B01

Trade Register: 08036741  
 +31 (0)577 456 345  
 info@veritex.nl

Our general terms and conditions are applied to all our offers, orders and agreements. A copy is available on [veritex.nl](http://veritex.nl) or on request.

Datasheet date: 11/2/2010

