

Specificatie CKX

Samenstelling

Drager : Polyester HT weefsel
Coating: Eenzijdig, weekgemaakte PVC
Dikte : -

95 gr/m²
270 gr/m²
365 gr/m² ±30

Eigenschappen

		Lengte	Breedte	
Treksterkte	DIN53354	1200 N/5cm	1000 N/5cm	± 25 %
Rek bij breuk	DIN53354	22 %	20 %	± 25 %
Scheursterkte	DIN53356	75 N	65 N	± 35 %
Hechting	DIN53357	> 50 N/5cm		
Waterdichtheid	DIN53886	> 100 cm		
Lichtechtheid	ISO 105	>= 7		
Koudebestendigheid	DIN53361	< -30 °C		

Wasvoorschrift



Handwas

Reinigen met vochtige doek en huishoudzeep.

Materiaal niet in contact brengen met oplosmiddelen/oplosmiddel houdende schoonmaakmiddelen.

Opmerkingen

Kleine kleur en glansverschillen onder voorbehoud (houd receptnummers gescheiden).

Kleurreproduceerbaarheid: unikleur <1, bedrukt <1.5, dual-kleur <2 (Delta E CIE-lab 1976 D65). Geen "doorzicht" kwaliteit

Datum: 26/9/2018

Specificatie datum: 7/11/2014

ABN AMRO BANK: 47.37.10.978
IBAN: NL94ABNA0473710978
BIC: ABNANL2A

ING BANK: 903250
IBAN: NL45INGB0000903250
BIC: INGBNL2A

BTW/VAT: NL005840247B01
Chamber of Commerce: 08036741

Our general terms and conditions are applied to all our offers, orders and agreements. A copy is available on request.



Management
System
ISO 9001:2015
www.tuv.com
ID 3108622561